

BISCO® RF-120

BISCO[®] RF-120 is a specialty silicone composite consisting of smooth aluminized fabric and low density BF-1000. It is a reflective foam designed to aid in heat management applications by both insulating against heat and reflecting it away, and is used in commercial, professional and military vehicles.

PROPERTY	TEST METHOD	TYPICAL VALUE	SPECIFICATION
PHYSICAL			
Color	VISUAL	WHITE	
Thickness Available, mm (inches)		2.50 ± 0.762 (0.098 ± 0.03) 5.00 ± 0.762 (0.197 ± 0.03)	
Areal Density, kg/m ² (lb./ft ²) 2.50 (0.098	") ASTM 146	0.83 (0.17)	0.25 max
5.00 (0.197	")	1.17 (0.24)	0.35 max
CFD Force Measured at 25% Deflection,	ASTM D1056	**41(6)	16.5 (2.4)
kPa (PS		**CFD is measured on foam only	0-35 (0-5)
*Tensile, kPa (PSI)	ASTM D412	138 (20)	
*Elongation, % min	ASTM D412	60	
Compression Set, % 22 hours, 100°C (212°F), 50% compression	ASTM D1056	35	
Cohesive Failure	INTERNAL	PASS	
Flammability, 4 in/min max	SAE J369		PASS
Temperature Range, C° (F°)	INTERNAL		-55°to+200° (-67°to 392°)



The information contained in this Data Sheet is intended to assist you in designing with Rogers' Elastomeric Material Solutions. It is not intended to and does not create any warranties, express or implied, including any warranty of merchantability or fitness for a particular purpose or that the results shown in this Data Sheet will be achieved by a user for a particular purpose. The user should determine the suitability of Rogers BISCO products for each application. The Rogers logo, BISCO, and the BISCO logo are trademarks of Rogers Corporation or one of its subsidiaries. © 2003, 2019, 2021 Rogers Corporation. All rights reserved. Printed in U.S.A., 0621-PDF • Publication #180-053 www.rogerscorp.com



PROPERTY	TEST METHOD	TYPICAL VALUE	SPECIFICATION
ELECTRICAL & THERMAL			
*Dielectric Strength, Volts/mil	ASTM D149	55	
*Dielectric Constant (1 kHz)	ASTM D150	1.6	
Dissipation Factor (1 kHz)	ASTM D150	0.0251	
Dry Arc Resistance, Seconds	ASTM D495	99	
Volume Resistivity, Ohm-cm	ASTM D257	10^16	
Thermal Conductivity, W/m °K	ASTM D518	0.067	

*Tensile, Elongation and Dielectric properties are tested with substrate.

Notes:

- All metric conversions are approximate.
- Additional technical information is available.
- Values should not be used for specification limits.



The information contained in this Data Sheet is intended to assist you in designing with Rogers' Elastomeric Material Solutions. It is not intended to and does not create any warranties, express or implied, including any warranty of merchantability or fitness for a particular purpose or that the results shown in this Data Sheet will be achieved by a user for a particular purpose. The user should determine the suitability of Rogers BISCO products for each application. The Rogers logo, BISCO, and the BISCO logo are trademarks of Rogers Corporation or one of its subsidiaries. © 2003, 2019, 2021 Rogers Corporation. All rights reserved. Printed in U.S.A., 0621-PDF • Publication #180-053 www.rogerscorp.com