

## DeWAL® DW215-3

DeWAL® DW215-3 is produced from skived PTFE film that is coated with a high temperature acrylic adhesive.

## Features & Benefits:

- Non-stick surface, low friction
- High temperature resistance
- Good Insulation

## Applications:

- Coil wraps
- Separators
- Transformers
- Slot liners
- Harness wrapping
- Composite bonding shops where silicone adhesive tapes are not permitted

PROPERTY	TEST METHOD	DATA RANGE	ТҮ	PICAL VALUE*
PHYSICAL				
Backing Material				PTFE Film
Backing Thickness, mm (inches)		0.069 - 0.084 (0.0027 - 0.0033)		
Adhesive System				Acrylic
Adhesive Thickness, mm (inches )		0.025 - 0.051 (0.001 - 0.002)		
Adhesion to Steel, g/cm (oz./in)	ASTM-D 3759	290 - 580 (26 - 52)		424 (38)
Tensile Strength, MPa (psi)	ASTM-D 3759	32 - 62 (4,716 - 8,933)		52 (7,561)
Elongation, %	ASTM-D 3759	(344 - 494)		435
Dielectric Strength, Volts/mil	ASTM-D 149	1,875 – 3,182		2,596
Maximum Operating Temperature, $C^{\circ}(F^{\circ})$				204 (400)
PRODUCT DIMENSIONS	METRI	C	ENGLISH	
Width mm, inches	12.7 - 546.1		0.5 - 21.5	
Core Diameter mm, inches	76		3	
Roll Length m, yards	33		36	

\*Typical values shown are from testing at date of manufacture and should not be used for specification limits.

- Additional technical information and product specifications are available upon request.

- Shelf life is 1 year from the date of manufacture with storage conditions of 21°C (70°F) and 50% RH.

- All metric conversions are approximate.



The information contained in this Data Sheet is intended to assist you in designing with Rogers' Elastomeric Material Solutions. It is not intended to and does not create any warranties, express or implied, including any warranty of merchantability or fitness for a particular purpose or that the results shown in this Data Sheet will be achieved by a user for a particular purpose. The user should determine the suitability of Rogers DeWAL products for each application. The Rogers logo, DeWAL logo and DeWAL are trademarks of Rogers Corporation or one of its subsidiaries. © 2019, 2020 Rogers Corporation. All rights reserved. 0120-PDF • Publication #175-141