

DeWAL[®] DW235 MSPU-Gray Laminate

DeWAL® DW235 MSPU-Gray is a laminate of extruded stabilized, pigmented PTFE bonded to polyurethane. It has the inherent benefits of PTFE with exceptional chemical resistance, crush resistance, reduced shrinkage, dimensional stability, low coefficient of friction, YaaV XVJ/[T[/[fk and nonstick properties.

FBG bdah[VV&S`V&e[1kTa`VST1WSkV&d_S][YfZ[e1S_[SfW [VV&^XadXSfUST1WVV&[Y`ež

Applications:

• Flat cable construction

Features	& Benefits:	
----------	-------------	--

- Exceptional chemical and crush resistance
- Dimensionally stable
- Low coefficient of friction
- Non-stick properties
- FBG 'SkWdbdah[VWéS Xge[`Y 'SkWdSei W^Se W h[da`_W fS^bdafWUf[a`

PROPERTY	TEST METHOD	TYPICAL VALUE*
Construction	N/A	ePTFE/TPU Film
Color	N/A	Gray
Tensile Strength, MPa (psi) PTFE Film	ASTM-D6040	20.6843 (2,000)
Elongation, % PTFE Film	ASTM-D6040	25
Total Thickness, cm (inches)	ASTM-D6040	0.045 (0.018)

PRODUCT DIMENSIONS	METRIC		ENGLISH	
Width cm, inches	2.54 – 15.24	Product Dependent	1 – 6	
Core Diameter cm, inches	7.62, 15.24		3, 6	
Maximum Roll O.D. cm, inches	17.78 - 45.72		7 - 18	
Core Type	Plastic or Cardboard			

*Typical values shown are from testing at date of manufacture and should not be used for specification limits.

- Additional technical information and product specifications are available upon request.

- Shelf life is 1 year from the date of manufacture with storage conditions of 21°C (70°F) and 50% RH.

- All metric conversions are approximate.



The information contained in this Data Sheet is intended to assist you in designing with Rogers' Elastomeric Material Solutions. It is not intended to and does not create any warranties, express or implied, including any warranty of merchantability or fitness for a particular purpose or that the results shown in this document will be achieved by a user for a particular purpose. The user should determine the suitability of Rogers DeWAL products for each application. The Rogers logo, DeWAL logo and DeWAL are trademarks of Rogers Corporation or one of its subsidiaries. © 2017, 2019 Rogers Corporation. All rights reserved. 1019-PDF • Publication #175-167